



HANAKYD HR-2016

(Alkyd resin)

TECHNICAL DATASHEET

PRINCIPAL PROPERTIES

- Good Gloss
- Weathering resistance
- Fast drying for NC type
- Chemical resistance

APPLICATIONS

- General purpose stoving enamel
- NC Lacquer

COMPOSITION

- Oil type : Soya bean fatty acid
- Solvent : Xylene

SPECIFICATION

- Appearance : Clear
- Non-volatile(%) : 58 ~ 60
- Viscosity(Gardner) : Z3 ~ Z5
- Acid value(Solid) : Max. 16
- Color(Gardner) : Max. 8

SOLUBILITY

- Mineral Spirit : Limited
- Toluene, Xylene : Complete
- Isopropyl alcohol : Complete
- n-BuOH : Complete
- Butyl Cellosolve : Complete
- n-Butyl acetate : Complete

COMPATIBILITY

- Long oil alkyd resin : Incompatible
- Medium oil alkyd resin : Incompatible
- Short oil alkyd resin : Complete
- Melamine resin : Complete
- Rosin modified maleic resin : Complete
- Nitro cellulose : Complete

PACKING

- 180kg Steel drum

HANDLING PRECAUTIONS

- Product safety information required for safe use is not included in this document.
- Before handling, read product and material safety data sheet and container labels for safe use, physical and health hazard information.