



## HANAKYD HR-2201

(Alkyd resin)

## TECHNICAL DATASHEET

### PRINCIPAL PROPERTIES

- Good water resistance
- Good gloss and gloss retention
- Good adhesive property

### APPLICATIONS

- Rust prevention coatings for steel structure
- Automotive under body coating

### COMPOSITION

- Oil type : Soya bean fatty acid
- Solvent : Mineral Spirit

### SPECIFICATION

- Appearance : Clear
- Non-volatile(%) : 49 ~ 51
- Viscosity(Gardner) : Z4 ~ Z6
- Acid value(Solid) : 10 ~ 20
- Color(Gardner) : Max. 10

### SOLUBILITY

- Mineral Spirit : Complete
- Toluene, Xylene : Complete
- Isopropyl alcohol : Complete
- n-BuOH : Complete
- Butyl Cellosolve : Complete
- n-Butyl acetate : Complete

### COMPATIBILITY

- Long oil alkyd resin : Complete
- Medium oil alkyd resin : Complete
- Short oil alkyd resin : Limited
- Melamine resin : Limited
- Rosin modified maleic resin : Limited
- Nitro cellulose : Limited

### PACKING

- 180kg Steel drum

### HANDLING PRECAUTIONS

- Product safety information required for safe use is not included in this document.
- Before handling, read product and material safety data sheet and container labels for safe use, physical and health hazard information.